

MUTUAL CORNELL

Irene and Danel
Farshine Jewelry Factory Co., Ltd
No. 4, Zhenlong Road, 5th Industrial Park Caiwu
Wusha, Chang'an Town, Dongguan City, Guizhou, China, 523850

December 2, 2021

CERTIFICATE OF ANALYSIS
Date Submitted: 11/30/2021

XRF Assay Composition

Sample Desc.: 14k 2.5mm Bezel CZ
Sample Date: 11/25/2021

Date Analyzed: 12/02/2021
Analyzed by: MS

Revised

	Results	Unit
Gold Tone Section		
Copper	30.852	%/wt.
Gold	58.530	%/wt.
Nickel	0.208	%/wt.
Silver	4.534	%/wt.
Zinc	5.876	%/wt.



Revision Note: Fixed the error with the results not feeding from the correct location. MS



Kevin E. Donahue
Laboratory Director



Jeff Mascoli
Laboratory Manager

The above results were obtained using a Fischer Technologies Fischerscope XAN-DPP-X-Ray Fluoroscope (XRF).

After grinding test results indicate the approximate assay composition of the substrate base metal only.

The measurement error is within +/- 5.0% of the measured values per typical instrumental methods.

Samples submitted by customer, results relate only to items tested.

Test report shall not be reproduced except in full, without written approval of the laboratory.

Pg. 1 of 1